Amendments to the Claims

This listing will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Previously Amended) A non-asphaltic underlayment comprising:

a glass fiber-based substrate in which a first surface thereof is directly adhered to a breathable thermoplastic film having a minimum thickness of 2 mils, the breathable thermoplastic film comprises a thermoplastic polyurethane blended with ethylene methacrylate polymer, wherein the ethylene methacrylate polymer acts as an adhesion improvement component that improves adhesion between the breathable thermoplastic film and the glass fiberbased substrate, said breathable thermoplastic film imparts water-resistance to the underlayment while maintaining breathablity thereof, the breathable thermoplastic film having a minimum moisture vapor transmission rate of greater than about 3 perms.

2. (Previously Amended) The non-asphaltic underlayment of claim 1 further comprising a skid-resistance component blended into the breathable thermoplastic film, the skid-resistance component comprising at least 1-10% of ethyl-vinyl acetate or maleic anhydride grafted ethyl-vinyl acetate.

3. (Previously Amended) The non-asphaltic underlayment of claim 1 further comprising a second breathable thermoplastic film located on a second surface of the glass fiber-based substrate.

(Previously Amended) The non-asphaltic underlayment of claim 1 wherein the substrate is woven or non-woven.

5. (Previously Amended) The non-asphaltic underlayment of claim 4 wherein the substrate is a non-woven glass-fiber based substrate.

6-8. (Cancelled).

Appl. No. 10/702,689 Amdt, Dated April 20, 2012

Response to Office Action of January 24, 2012

9. (Original) The non-asphaltic underlayment of claim 1 wherein the substrate has a thickness from about 5 to about 60 mils.

10-11. (Cancelled)

12. (Previously Amended) The non-asphaltic underlayment of claim 1 wherein the breathable thermoplastic film has a thickness of about 2 to about 10 mils.

13-15. (Cancelled)

16. (Previously Amended) The non-asphaltic underlayment of claim 1 further comprising at least one of a water repellent material, an algaecide, an herbicide, an antifungal material, a surface friction agent, a flame retardant, or a coloring dye.

17. (Original) The non-asphaltic underlayment of claim 1 wherein the underlayment is a base sheet of a peel and stick roofing product.

18. (Previously Amended) A non-asphaltic underlayment comprising a substantially non-water-resistant polypropylene substrate in which at least a top surface thereof is directly adhered to a polyurethane based thermoplastic film, said polyurethane based thermoplastic film imparts water-resistance to the underlayment while maintaining breathability of the underlayment, the breathable thermoplastic film having a minimum moisture vapor transmission rate of 3 perms or greater the polyurethane based thermoplastic film being blended with about 40 to 60% ethylene methacrylate polymer to improve adhesion between the polyurethane based thermoplastic film and the substantially non-water-resistant polypropylene substrate.

19-35. (Cancelled)

36. (Previously Presented) The non-asphaltic underlayment of claim 2 wherein the skid-resistance component is a surface friction agent.

Appl. No. 10/702,689 Amdt, Dated April 20, 2012

Response to Office Action of January 24, 2012

37. (Previously Amended) A non-asphaltic underlayment comprising:

a breathable thermoplastic film comprising a thermoplastic polyurethane blended with

ethylene methacrylate polymer, the ethylene methacrylate polymer acting as an adhesion

improvement component; and

a substrate, the substrate having a thickness of about 6 to 60 mils, the substrate being air

sprayed with more than two mils but less than 10 mils of the breathable thermoplastic film,

wherein the breathable thermoplastic film imparts water-resistance to the underlayment while

maintaining breathability thereof as defined in ASTM E96 standard.

38. (Currently Amended) The non-asphaltic underlayment of claim 37 4 further

comprising a skid-resistance component blended into the breathable thermoplastic film, the skid-

resistance component comprising at least 1-10% of ethyl-vinyl acetate or malefic anhydride

grafted ethyl-vinyl acetate.

39. (Currently Amended) The non-asphaltic underlayment of claim 37 4 further

comprising a second breathable thermoplastic film air sprayed onto a second surface of the

substrate.

40. (Currently Amended) The non-asphaltic underlayment of claim <u>37</u> 4 wherein the

substrate is nonwoven polypropylene.

41. (Currently Amended) The non-asphaltic underlayment of claim <u>37</u> [‡] further

comprising a water repellent material, an algaecide, an herbicide, an antifungal material, a

surface friction agent, a flame retardant, a coloring dye and combinations thereof.

42. (Currently Amended) The non-asphaltic underlayment of claim <u>37</u> 4 wherein the

underlayment is a base sheet of a peel and stick roofing product.

4 of 6